

PRODUCT SPECIFICATION

Cyanoacrylate Activator

Description

This product is an aerosol applied cyanoacrylate accelerant, which once applied to a difficult to bond substrate, significantly increases the cure speed of cyanoacrylate adhesive. The product is used primarily on wood mitre joints or on porous, acidic or difficult to bond surfaces.

Achieve an instant bond with no mess. Allow 10 seconds for positioning. Bonds to MDF, wood, chipboard, rubber, metals, most plastics, perspex, ceramics, aluminium and much more. Perfect for all cornice and profile mitres, trims, picture frames, MDF skirting and architrave joints, worktop end strips, PVCu trims and much more.

Technical Data

Consistency:	Liquid
Colour	Colourless
Specific gravity (DIN 53479)	Approx. 0.79 g/cm ³
VOC Level	605 g/l (grams/liter)
Solvent	<ul style="list-style-type: none">• LOW BOILING POINT MODIFIED NAPHTHA - NAPHTHA (PETROLEUM), SOLVENT-REFINED LIGHT• PROPANE• BUTANE• ISOBUTANE

Directions For Use

1. Ensure both surfaces to be bonded are clean, dry and free from grease.
2. Lightly spray one of the surfaces to be bonded with the activator.
3. Allow the activator to dry.
4. Apply a thin layer of the cyanoacrylate to the other surface.
5. Bring both surfaces together to achieve a bond. Depending on the substrates being used and temperature a rapid bond will be typically formed in 2-10 seconds.

Storage and Shelf Life

The activator should be stored between 5 and 30 degrees centigrade, away from direct sunlight. The aerosol has 12 months shelf life.

Health and Safety

Extremely flammable. Keep in well ventilated place away from sources of ignition. Do not breathe vapour or empty in drains. Do not pierce or burn after use.

**For further Health and Safety information - see separate MSDS sheet.*

Disclaimer: All the information in the Data Sheet is based on practical experience and is published in good faith. However, because we have no control over the manner or conditions in which our products are used, or over work undertaken or end product manufactured by the purchaser, we cannot accept liability for results. Responsibility for ascertaining the suitability of products for his purposes rests with the purchaser. All conditions, representations, statements, warranties or guarantees whatsoever, whether express, implied or statutory, in respect of any goods manufactured, sold or supplied by us are hereby expressly excluded and we accept no liability in respect of any claim for damage or consequential loss caused to any property arising directly or indirectly out of the use of our products or goods.

Revision date: 09/2023 - Revision: 04



TDS **Cyanoacrylate** **Activator**