

STICKFAST MPS
Hotmelt Gluesticks

FEATURES

- ◆ Versatile adhesion
- ◆ Multi-purpose use
- ◆ Medium to long set time
- ◆ Clear

APPLICATIONS

- ◆ Upholstery and foam bonding
- ◆ Fabric bonding
- ◆ Multi-purpose assembly
- ◆ Display packaging

PROPERTIES	SPECIFICATIONS (TYPICAL VALUES)
Colour	Clear
Form	12mm,18mm, 43mm Sticks
Softening Point, °C, Ring & Ball	86° C
Viscosity @ 190°C	8,750cPs
Open Time	Medium to Long

Application Equipment

Stickfast hotmelts can be applied through most glue guns, however for best performance use genuine Stickfast glue guns.

Application Temperature

180°C - 195°C (depending on application)

FDA approval

All constituent parts of this adhesive have been approved by the American F.D.A under CFR 21.175.105 (adhesives)

Packaging:

Product Code: MPS12 / MPS18 / MPS43
5kg Boxes / 20kg outer
600 kg per pallet

Health & Safety

For handling and processing precautions, please consult the corresponding Material Safety Data Sheet.

IMPORTANT NOTICE

IMPORTANT NOTICE: The data herein is furnished for information purposes only, and is believed to be reliable. Acculyte Industrial and any of its subsidiary companies cannot assume responsibility for the results obtained by others, over whose methods it does not control. It is the users responsibility to determine suitability for the user's intended purpose of any product and any product method mentioned herein, and to adopt any such precautions as may be necessary to protect property and persons against any hazards that may be involved in the handling and use thereof. We recommend that each prospective user test the proposed application to determine the suitability of this product for the purpose intended prior to incorporating any product or application in its manufacturing process using this data as a guide. Acculyte Industrial accept no liability arising out of the use of this information or the products described herein. This technical data sheet is covered by copyright and must not be reproduced or copied in part or in whole by photocopying, electric reproduction, mechanical reproduction or any other means, without the written permission of Acculyte Industrial. This data sheet supersedes all previous data sheets.

Revision Date 03/03/2011